

WOVEN FABRIC

Product Description: **GG-160 P**
Carbon Fabric

CHARACTERISTICS	NOMINAL	UM	TOLERANCE	NORMATIVE
Mass unit per area	160	g/m ²	5,0%	ISO 3374
Weave	Plain			ISO 2113
Width	from 100 to 1270	mm	2,5%	ISO 22198
Thickness	0,15	mm	5,0%	ISO 5084 (**)
Other informations	Loomstate			

NOMINAL CONSTRUCTION	WARP		WEFT	
1st fiber description	HS Carbon Fiber - HexTow AS4C - 3K		HS Carbon Fiber - HexTow AS4C - 3K	
1st fiber producer	HEXCEL		HEXCEL	
2nd fiber description				
2nd fiber producer				
Thread count - 1st fiber	4,00 ends/cm ±2%	ISO 4602	4,00 ends/cm ±2%	ISO 4602
Thread count - 2nd fiber				
Weight distribution - 1st fiber	80 g/m ²	50,0%	80 g/m ²	50,0%
Weight distribution - 2st fiber				
Weight distribution	50,0%		50,0%	
Selvages	Weaving style	LENO	Type of fiber	HM polyster 22 tex

MECHANICAL PROPERTIES OF FIBER	STRENGHT (nominal)	MODULUS (nominal)
HexTow AS4C - 3K	4550 MPa	231 GPa

(**) Theoretical thickness for an epoxy laminate with 40% of reinforcement in volume.

Note: Technical information furnished is based on laboratory findings and believed to be correct. No warranties of any kind are made except that the materials supplied are of standard quality. All risk and liabilities arising from handling, storage and use of products, as well as compliance with applicable legal restrictions, rests with the user.

ANGELONI GROUP

Via Abbate Tommaso 72/A 30020 Quarto D'Altino (VE) - Italy
T. +39 0422 780580 - F. +39 0422 782787
E. info@angelonigroup.com

angelonigroup.com