



**Product Data Sheet** 

## **Textile Reinforcement for High Performance Composite**

HexForce® reinforcements are available in a range of weave styles – from woven fabrics to multiaxials and specialties that offers a range of globally certified aerospace / industrial products in carbon, glass and aramid and specialty fibers that we sell under the HexForce® trademark.

DESCRIPTION		SI Units	US Units	
Type of yarns	Warp	HexTow AS	HexTow AS4C GP 3K	
	Weft	HexTow AS4C GP 3K		
Nominal weight		200 g/m²	5.9 oz/sqy²	
Weave style		TWILL 2/2		
Width		1250 mm	49.2 in	
Finish type				
Finish description				

CHARACTERISTICS		SI Units	US Units	
Nominal construction	Warp	5 yarn/cm	12.70 yarn/in	
	Weft	5 picks/cm	12.7 picks/in	
Weight distribution	Warp	50 %		
	Weft	50	50 %	
Thickness (*)		0.2 mm	0.008 in	

<sup>\*</sup>NB: The above average values are obtained with laminate at 55% of fibres in volume.

## For more informations

Hexcel is a leading worlwide supplier of composite materials to aerospace and industrial markets. Our comprehensive range includes:

- HexTow® carbon fibers

- HexMC® molding compounds

- Acousti-CAP® sound

HexForce® reinforcements

- HexFlow® RTM resins

attenuating honeycomb

- HiMax™ multiaxial reinforcements

- Redux® adhesives

- Engineered core

- HiTape™ advanced reinforcements

- HexTool® tooling materials

- Engineered products

- HexPly® prepregs

- HexWeb® honeycombs

For US quotes, orders and product information call toll-free 1-800-688-7734. For other worldwide sales office telephone numbers and a full address list, please go to:

## http://www.hexcel.com/contact/salesoffice

© 01/10/2018 | Hexcel Corporation - All rights reserved. Hexcel Corporation and its subsidiaries ("Hexcel") believe that the technical data and other information provided herein was materially accurate as of the date this document was issued. Hexcel reserves the right to update, revise or modify such technical data and information at any time. Any performance values provided are considered representative but do not and should not constitute a substitute for your own testing of the suitability of our products for your particular purpose. HEXCEL MAKES NO WARRANTY OR REPRESENTATION, EXPRESS OR IMPLIED, INCLUDING BUT NOT LIMITED TO THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, AND DISCLAIMS ANY LIABILITY ARISING OUT OF OR RELATED TO, THE USE OF OR RELIANCE UPON ANY OF THE TECHNICAL DATA OR INFORMATION CONTAINED IN THIS DOCUMENT.