



SELCOM SRL via della Torre n. 17 31010 FREGONA (TV) ITALY

phone +39 0438 585166 modem fax +39 0438 585172 manual fax +39 0438 916049 cap. soc. EURO 101490,00 cod. fisc. e p.i. IT 02369430265 trib. Treviso n. 33642 reg. soc. c.c.i.a.a. Treviso n. 206094 M. estero TV 028944 E-mail: info@selcom-srl.com

MULTIAXIAL TECHNOLOGY (NCF) unidirectional & stitched multiaxial fabrics in glass, carbon, aramid... and hybrids for the composite industry

internet: www.selcom-srl.com

Technical Data Sheet

PRODUCT NAME CEQX600 – 2	Code
Quadriaxial fabric 0° +45° 90° -45° hybrid in "E" glass and carbon fibre	23600000637

layers	angle	fibre	plan	tex	areal weight	areal weight
	tolerance				gr/m²	tolerance
Oº	-	Polyester yarn	L2	8,0	11	± 3 %
Oº	± 1º	E glass : PPG Roving 2002 or equivalent	L2	300	89	± 3 %
Oº	± 1º	Carbon : 12K Toray T700SC 50C or equivalent	L2	800	79	± 3 %
- 45º	± 1º	E glass : PPG Roving 2002 or equivalent	L2	200 - 136	98	± 3 %
- 45º	± 1º	Carbon: 12K Toray T700SC 50C or equivalent	L2	800	56	± 3 %
90º	± 1º	E glass : PPG Roving 2002 or equivalent	L2	300	100	± 3 %
90º	± 1º	Carbon: 12K Toray T700SC 50C or equivalent	L2	800	50	± 3 %
+ 45º	± 1º	E glass : PPG Roving 2002 or equivalent	L2	200 - 136	98	± 3 %
+ 45º	± 1º	Carbon : 12K Toray T700SC 50C or equivalent	L2	800	56	± 3 %
		TOTAL gr/m²	-	-	637	± 3 %

Characteristics for fabric

Characteristics for fabric	
standard roll length:	mtl 50 ± 1 mtl
standard roll width:	mm 1270 ± 10 mm
net roll weight:	Kg. 40,5 ± 3 %
areal weight tolerance:	$\pm 3\% (\pm 19 \mathrm{gr/m^2})$
theoretical areal weight:	gr/m² 637
ident roll:	CEQX600 - 2
knitting type:	catenella + tricot
stitch yarn:	polyester, texturated, 78 dtex

Characteristics for filament varn

	PPG Roving 2002	T700SC - 50C -12K
binder content:	0.55 – 0.65 % (nominal)	0.9 – 1.0 %
produttore – manufacturer:	PPG Industries	Toray Industries Inc.
densità volumetrica – volumetric density:	gr/cm³ 2.59 – 2.62	g/cm ³ 1.80
nr. filamenti – number of filaments:	n.d.	12000
resistenza a trazione – tensile strength:	Mpa 1900 – 2400 (ASTM D-2343) *	Mpa 4800 - 5000**
modulo a trazione – tensile modulus:		Gpa 230**
allungamento a rottura – elongation at break:	3.5 - 4 %	2.20 %**

^{*} Determined from resin impregnated rovings according to ASTM D-2343**Measured using the impregnated strand test method. These informations can be used for material selection purposes only. Fregona lì 14/09/16

NB: THIS DOCUMENT IS COMPUTER GENERATED AND IT'S VALID WITHOUT SIGNATURE. Ing. Giovanni Fardin

SELCOM Srl is a weaver of technical textiles from continuous filaments (rovings). All information supplied by or on behalf of SELCOM Srl in relation to its products, whether in the nature of data, recommendations or otherwise, has been given in good faith and in compliance with technical and commercial information supplied by raw materials (fibre) manufacturers. All information aforementioned are supported by its own experience and believed reliable but SELCOM Srl declines all responsibility in respect of the application, processing ore use of the aforementioned information or any consequence thereof. The buyer undertakes all liability in respect of the application, processing or use of the aforementioned information or product, whose quality and other properties he shall verify or any consequence thereof. SELCOM Srl believes that it is the user that shall determine the suitability of a product for its end-use and the user that assures all liability in connection therewith.

