



SELCOM

Multiaxial Technology

SELCOM SRL
 via della Torre n. 17
31010 FREGONA (TV) ITALY
 phone +39 0438 585166
 modem fax +39 0438 585172
 manual fax +39 0438 916049

cap. soc. EURO 101490,00
 cod. fisc. e p.i. IT 02369430265
 trib. Treviso n. 33642 reg. soc.
 c.c.i.a.a. Treviso n. 206094
 M. estero TV 028944
 E-mail: info@selcom-srl.com

MULTIAXIAL TECHNOLOGY (NCF)
 unidirectional & stitched multiaxial fabrics in
 glass, carbon, aramid... and hybrids for the
 composite industry

internet: www.selcom-srl.com

Technical Data Sheet

PRODUCT NAME KEBXS600M200

Code Nr. 22312000607

Biaxial fabric 0° 90° hybrid in "E" glass and aramid fibre
 stitched with chopped strand mat

layers	angle	fiber	plan	tex	areal weight	areal weight
	tolerance				gr/m ²	tolerance
0°	-	Polyester yarn	L5 - L4	8,3	10	± 3 %
0°	± 1°	E glass : PPG Roving 2002 or equivalent	L5 - L4	1200 - 2400	208	± 3 %
0°	± 1°	Twaron 2200	L5 - L4	340	103	± 3 %
90°	± 1°	E glass : PPG Roving 2002 or equivalent	L5 - L4	600	183	± 3 %
90°	± 1°	Twaron 2200	L5 - L4	340 - 170	103	± 3 %
random	-	E glass : PPG Roving 7864/6800 or equivalent	L5 - L4	2600 - 2400	200	± 3 %
		TOTAL grm²	-	-	807	± 3 %

Characteristics for fabric

lunghezza rotolo - standard roll length:	mtl 50 ± 1 mtl
larghezza rotolo - standard roll width:	mm 1270 ± 10 mm
peso netto rotolo - net roll weight:	Kg. 51,5 ± 3 %
tolleranza sulla grammatura - areal weight tolerance:	± 3 % (± 24 gr/m ²)
grammatura teorica - theoretical areal weight:	gr/m ² 807
identificazione rotolo - ident roll:	KEBXS600M200
tipo di legatura - knitting type:	chain + tricot
filo di legatura - stitch yarn:	polyester, texturated, 8,3 tex

Characteristics for filament yarn

tipo fibra - type:	Twaron 2200	PPG Roving 2002
binder content:	0.90%	0.55 - 0.65 % (nominal)
produttore - manufacturer:	Teijin Twaron b.v.	PPG Industries
densità volumetrica - volumetric density:	g/cm ³ 1,44	gr/cm ³ 2.59 - 2.62
diamentro filamento - filament diameter:	µm 12 - µm 17	µm 12 - µm 15 - µm 17
resistenza a trazione - tensile strength:	Mpa 3150**	Mpa 1900 - 2400 (ASTM D-2343) *
modulo a trazione - tensile modulus:	Gpa 110**	Gpa 69 - 76 (ASTM D-2343) *
allungamento a rottura - elongation at break:	2.7%**	3.5 - 4 %

* Determined from resin impregnated rovings according to ASTM D-2343. **Measured according Test Methodes of Twaron O5.92.0358. These informations can be used for material selection purposes only.
 Fregona lì 04/06/14

Quality Assurance
 Ing. Giovanni Fardin

NB : THIS DOCUMENT IS COMPUTER GENERATED AND IT'S VALID WITHOUT SIGNATURE

Confidentiality Statement

The information, data, and charts embodied in this Technical Data Sheet (TDS) are strictly confidential and are supplied on the understanding that they will be held confidentially and not disclosed to third parties without the prior written consent of Selcom srl with registered office in 31010 Fregona (TV) ITALY-Via Della Torre no. 17 -For further info, please contact Selcom srl at info@selcom-srl.com or fax to no. +39 0438 58 51 72 / 91 60 49.

SELCOM Srl is a weaver of technical textiles from continuous filaments (rovings). All information supplied by or on behalf of SELCOM Srl in relation to its products, whether in the nature of data, recommendations or otherwise, has been given in good faith and in compliance with technical and commercial information supplied by raw materials (fibre) manufacturers. All information aforementioned are supported by its own experience and believed reliable but SELCOM Srl declines all responsibility in respect of the application, processing or use of the aforementioned information or any consequence thereof. The buyer undertakes all liability in respect of the application, processing or use of the aforementioned information or product, whose quality and other properties he shall verify or any consequence thereof. SELCOM Srl believes that it is the user that shall determine the suitability of a product for its end-use and the user that assures all liability in connection therewith.

☐ M10-1-02.DOC Ed.01-Rev.00-12.05.10

