



SPECIFICATION OF CHOPPED STRAND MAT TGFM 600P

| ITEM | | SPECIFICATION |
|----------------------------|-----|---------------|
| GLASS TYPE | | E-GLASS |
| BONDED TYPE | | POWDER |
| 0.1 m ² WEIGHT | g | 48.0 - 72.0 |
| L.O.I. | % | 3.0 ± 1.2 |
| TENSILE IND. (150mmx270mm) | Kgf | > 7.0 |
| LOOSE SURFACE | % | < 0.30 |
| MOISTURE | % | < 0.20 |
| WIDTH (1 SIDE TRIMMED) | mm | - 0 / + 30 |
| (2 SIDE TRIMMED) | mm | ± 3 |
| ALKALI CONTENT | % | < 0.80 |
| FILAMENT DIA. | μ m | 12 |
| APPEARANCE | | GOOD |
| COMPATIBLE RESIN | | UP / VE |

UPDATE : 2010-09-20

STORAGE CONDITIONS

*It is recommended to store glass fibre products in a cool dry area. Temperature should not exceed 35°C and the relative humidity should be kept below 75 %. suitable Temp.: 21 ± 11 °C , R.H. 60 ± 20 %. Glass fibre products must remain in packaging material until just prior to its use. Validity : We recommend this product should be used within 12 months from the delivery date to ensure optimum performance. Do not stack pallets higher than two.

Kuo, M. C.

Q/C Assistant Manager