



SELCOM SRL via della Torre n. 17 31010 FREGONA (TV) ITALY phone +39 0438 585166

modem fax +39 0438 585166 manual fax +39 0438 916049 cap. soc. EURO 101490,00 cod. fisc. e p.i. IT 02369430265 trib. Treviso n. 33642 reg. soc. c.c.i.a.a. Treviso n. 206094 M. estero TV 028944 E-mail: info@selcom-srl.com

MULTIAXIAL TECHNOLOGY (NCF) unidirectional & stitched multiaxial fabrics in glass, carbon, aramid... and hybrids for the composite industry

internet: www.selcom-srl.com

Technical Data Sheet

PRODUCT NAME EBXS600 Biaxial fabric 0º 90º in "E" glass

Code 01300000612

| layers | fiber | plan | tex | areal weight | areal weight |
|--------|---|------|-----------|--------------|--------------|
| | | | | gr/m² | tolerance |
| Oº | E glass : PPG Roving 2002 or equivalent | M2 | 900 - 600 | 300 | ± 3 % |
| 90º | E glass : PPG Roving 2002 or equivalent | M2 | 900 - 600 | 300 | ± 3 % |
| Oº | polyester | M2 | 8,3 | 12 | ± 3 % |
| | TOTAL gr/m² | - | - | 612 | ± 3 % |

Characteristics for fabric

| Sharacter 1808 161 145116 | | | | |
|---|-----------------------------------|--|--|--|
| lunghezza rotolo - standard roll length: | mtl 50 ± 1 mtl | | | |
| larghezza rotolo - standard roll width: | mm 1270 ± 10 mm | | | |
| peso netto rotolo - net roll weight: | Kg. 39 ± 3 % | | | |
| tolleranza sulla grammatura – areal weight tolerance: | $\pm 3\% (\pm 18 \text{ gr/m}^2)$ | | | |
| grammatura teorica – theoretical areal weight: | gr/m² 612 | | | |
| identificazione rotolo - ident roll: | EBXS600 | | | |
| tipo di legatura - knitting type: | tricot | | | |
| filo di legatura – stitch yarn: | polyester, texturated, 8,3 tex | | | |
| | | | | |

Characteristics for filament varn

| end determented for marrierit yarri | | | | |
|---|-----------------------------------|--|--|--|
| tipo fibra – type: | PPG Roving 2002 | | | |
| binder content: | 0.55 – 0.65 % (nominal) | | | |
| produttore – manufacturer: | PPG Industries | | | |
| densità volumetrica – volumetric density: | gr/cm ³ 2.59 – 2.62 | | | |
| diamentro filamento – filament diameter: | μm 12 - μm 15 | | | |
| resistenza a trazione – tensile strength: | Mpa 1900 – 2400 (ASTM D-2343) * | | | |
| modulo a trazione – tensile modulus: | Gpa 69 – 76 (ASTM D-2343) * | | | |
| allungamento a rottura – elongation at break: | 3.5 - 4 % | | | |

^{*} According to ASTM D-2343. All these informations can be used for material selection purposes only.

Fregona lì 02/12/14

Technical Manager Ing. Giovanni Fardin

NB: THIS DOCUMENT IS COMPUTER GENERATED AND IT'S VALID WITHOUT SIGNATURE



DNV-GL TYPE APPROVED PRODUCT - Cert. No. TAKOOOO17W

