



SELCOM SRL via della Torre n. 17 31010 FREGONA (TV) ITALY phone +39 0438 585166

modem fax +39 0438 585172 manual fax +39 0438 916049

cap. soc. EURO 101490.00 cod. fisc. e p.i. IT 02369430265 trib. Treviso n. 33642 reg. soc. c.c.i.a.a. Treviso n. 206094 M. estero TV 028944 E-mail: info@selcom-srl.com

MULTIAXIAL TECHNOLOGY (NCF) unidirectional & stitched multiaxial fabrics in glass, carbon, aramid... and hybrids for the composite industry

internet: www.selcom-srl.com

Technical Data Sheet

PRODUCT NAME EBXS800M100

Code

Biaxial fabric 0º 90º in "E" glass stitched with chop strand mat 01311000808

layers	angle	fiber	plan	tex	areal weight	areal weight
	tolerance				gr/m²	tolerance
Oo	-	Polyester yarn	L5	8,0	6	± 3 %
Oº	± 1º	E glass : PPG Roving 2002 or equivalent	L5	1200 - 600	402	± 3 %
90º	± 1º	E glass : PPG Roving 2002 or equivalent	L5	1200 - 600	400	±3%
random	-	E glass : PPG/OCV chop roving or equiv.	L5	2400 - 2600	100	± 3 %
		TOTAL gr/m²	-	-	908	± 3 %

Characteristics for fabric

91141 4 C C C 1 C C C C C C C C C C C C C						
lunghezza rotolo - standard roll length:	mtl 50 ± 1 mtl					
larghezza rotolo - standard roll width:	mm 1270 ± 20 mm					
peso netto rotolo - net roll weight:	Kg. 58 ± 3 %					
tolleranza sulla grammatura – areal weight tolerance:	$\pm 3\% (\pm 27 \text{ gr/m}^2)$					
grammatura teorica - theoretical areal weight:						
identificazione rotolo - ident roll:	EBXS800M100					
tipo di legatura - knitting type:	tricot					
filo di legatura – stitch yarn:	polyester, texturated, 8,0 tex					

Characteristics for filament yarn

tipo fibra – type:	PPG Roving 2002		
binder content:	0.55 – 0.65 % (nominal)		
produttore – manufacturer:	PPG Industries		
densità volumetrica – volumetric density:	gr/cm ³ 2.59 – 2.62		
diamentro filamento – filament diameter:	μm 12 - μm 15 - μm 17		
resistenza a trazione – tensile strength:	Mpa 1900 – 2400 (ASTM D-2343) *		
modulo a trazione – tensile modulus:	Gpa 69 – 76 (ASTM D-2343) *		
allungamento a rottura – elongation at break:	3.5 - 4 %		

^{*}According to ASTM D-2343. All these informations can be used for material selection purposes only.

Fregona lì 17/10/18 Technical Manager Ing. Giovanni Fardin

NB: THIS DOCUMENT IS COMPUTER GENERATED AND IT'S VALID WITHOUT SIGNATURE



DNV-GL TYPE APPROVED PRODUCT - Cert. No. TAKOOOO17W



Confidentiality Statement

The information, data, and charts embodied in this Technical Data Sheet (TDS) are strictly confidential and are supplied on the understanding that they will be held confidentially and not disclosed to third parties without the prior written consent of Selcom srl with registered office in 31010 Fregona (TV) ITALY-Via Della Torre no. 17 –For further info, please contact Selcom srl at info@selcom-srl.com or fax to no. +39 0438 58 51 72 / 91 60 49 SELCOM SrI is a weaver of technical textiles from continuous filaments (rovings). All information supplied by or on behalf of SELCOM SrI in relation to its products, whether in the nature of data, recommendations or otherwise, has been given in good faith and in compliance with technical and commercial information supplied by raw materials (fibre) manufacturers. All information aforementioned are supported by its own experience and believed reliable but SELCOM SrI declines all responsibility in respect of the application, processing ore use of the aforementioned information or any consequence thereof. The buyer undertakes all liability in respect of the application, processing or use of the aforementioned information or product, whose quality and other properties he shall verify or any consequence thereof. SELCOM Srl believes that it is the user that shall determine the suitability of a product for its end-use and the user that assures all liability in connection therewith. 🖫 M10-1-02.DOC Ed.01-Rev.00-12.05.10