



# SELCOM

## Multiaxial Technology

**SELCOM SRL**  
 via della Torre n. 17  
 31010 FREGONA (TV) ITALY  
 phone +39 0438 585166  
 modem fax +39 0438 585172  
 manual fax +39 0438 916049

cap. soc. EURO 101490,00  
 cod. fisc. e p.i. IT 02369430265  
 trib. Treviso n. 33642 reg. soc.  
 c.c.i.a.a. Treviso n. 206094  
 M. estero TV 028944  
 E-mail: [info@selcom-srl.com](mailto:info@selcom-srl.com)

**MULTIAXIAL TECHNOLOGY (NCF)**  
 unidirectional & stitched multiaxial fabrics in  
 glass, carbon, aramid... and hybrids for the  
 composite industry

internet: [www.selcom-srl.com](http://www.selcom-srl.com)

## Technical Data Sheet

<b>PRODUCT NAME EQX1500M300</b> Quadriaxial fabric 0° +45° 90° -45° in "E" glass stitched with chop strand mat
---

layers	angle tolerance	fiber	tex	areal weight gr/m <sup>2</sup>	areal weight tolerance
0°	-	Polyester yarn	8,0	9	± 3 %
0°	± 2°	E glass roving : NEG Hybon 2002 or equivalent	2400 - 1200	602	± 3 %
+45°	± 2°	E glass roving : NEG Hybon 2002 or equivalent	300 - 600	299	± 3 %
90°	± 2°	E glass roving : NEG Hybon 2002 or equivalent	1200	300	± 3 %
-45°	± 2°	E glass roving : NEG Hybon 2002 or equivalent	300 - 600	299	± 3 %
random	-	E glass : chop roving OCV M3060 or equivalent	2400	300	± 3 %
TOTAL gr/m <sup>2</sup>			-	1809	± 3 %

### Characteristics for fabric

standard roll length:	mtl 50 ± 1 mtl
standard roll width:	mm 1270 ± 20 mm
net roll weight:	Kg. 115 ± 3 %
areal weight tolerance:	± 3 % ( ± 54 gr/m <sup>2</sup> )
theoretical areal weight:	gr/m <sup>2</sup> 1809
ident roll / selcom prod. ident:	<b>EQX1500M300</b>
knitting type:	tricot
stitching yarn type:	polyester, texturised, 8.0 tex

### Characteristics for fibre

fibre type:	Hybon 2002
binder content:	0.55 - 0.65 % ( nominal )
manufacturer:	NEG - Nippon Electric Glass
volumetric density:	gr/cm <sup>3</sup> 2.59 - 2.62
filament diameter:	µm 17 - µm 15 - µm 14
tensile strength:	Mpa 1900 - 2400 ( ASTM D-2343 ) *
tensile modulus:	Gpa 69 - 76 ( ASTM D-2343 ) *
elongation at break:	3.5 - 4 %

\* According to ASTM D-2343. All these informations can be used for material selection purposes only.

NB : THIS DOCUMENT IS COMPUTER GENERATED AND IT'S VALID WITHOUT SIGNATURE

Fregona li 22/12/2023

Technical Manager  
 Ing. Giovanni Fardin



DNV-GL TYPE APPROVED PRODUCT - Cert. No. TAK000017Y



SELCOM Srl is a weaver of technical textiles from continuous filaments (rovings). All information supplied by or on behalf of SELCOM Srl in relation to its products, whether in the nature of data, recommendations or otherwise, has been given in good faith and in compliance with technical and commercial information supplied by raw materials (fibre) manufacturers. All information aforementioned are supported by its own experience and believed reliable but SELCOM Srl declines all responsibility in respect of the application, processing or use of the aforementioned information or any consequence thereof. The buyer undertakes all liability in respect of the application, processing or use of the aforementioned information or product, whose quality and other properties he shall verify or any consequence thereof. SELCOM Srl believes that it is the user that shall determine the suitability of a product for its end-use and the user that assures all liability in connection therewith. M10-1-02.DOC Ed.01-Rev.00-12.05.10