



HexPly[®] Epoxy Matrix M9.6GF/37%/300H8/G



Product Data Sheet

Description

HexPly[®] M9.6GF/37%/300H8/G is a Epoxy E-Glass Woven prepreg, whereby M9.6GF is the resin type; 37% is the resin content by weight; 300H8/G is the reinforcement reference and G represents E-Glass fibre. This data sheet is complementary to the M9.6GF resin data sheet, which should be consulted for additional information.

Reinforcement Data				0°	90°		
Nominal Area Weight	g/m ²	300	153	147			
Composition	8H satin						
Fibre Type	E-Glass						
Nominal Fibre Density	g/cm ³	2,6					

Matrix Properties			
Glass transition temperature of laminate	°C	110°C +/-5°C (ISO 11357-2, 10°C/min, -40 to 270°C)	
(Cure cycle: 30 min @ 120°C)			
Nominal Resin Density	g/cm ³	1.1 - 1.2 (ISO 1183-1)	

Prepreg Data			
Nominal Area Weight	g/m ²	477	
Nominal Resin Content	weight %	37	
Volatiles	weight %	Hot Melt	
Tack Level		Medium	

Processing			
Cure Cycle		@ 100 °C	*70 +/-15 min
	or	@ 110 °C	*45 +/-10 min
	or	@ 120 °C	*33 +/-7 min
Recommended heat up rate	°C/min	0.5 - 5	
Pressure gauge	bar	0.5 - 5	


The optimum cure cycle, heat up rate and dwell period depend on part size, laminate construction, oven capacity and thermal mass of tool.

*Time to 95% conversion


Cured Laminate Properties

(nominal composite density 1,8 g/cm³)

RESIN CONTENT % vs CURED PLY THICKNESS



RESIN CONTENT % vs FIBRE VOLUME %



The above graphs enable the fibre volume content of a laminate to be estimated using the measured cured ply thickness. The calculation assumes no resin loss.



HexPly® Epoxy Matrix M9.6GF/37%/300H8/G



Mechanical Properties

Mechanical Properties are based on 120 °C cure for 60 min, at 0,9 bar vacuum.

Data is the result from several tests on Vacuum bag cured laminates. Some of the values achieved will have been higher, and some lower (15 %), than the figure quoted.

(Normalised to 50% fibre volume, except for ILSS)

0° (RT / Dry)	Tensile	Flexural	ILSS	Compression
Strength (MPa)	520	610	50	
Modulus (GPa)	25,6	21,2	.	
Test Method	EN ISO 527	ISO 14125	ISO 14130	

Prepreg Storage Life

Shelf Life¹: 18 months at -18°C/0°F (from date of manufacture).

¹ Shelf Life: the maximum storage life for HexPly® prepreg, when stored continuously, in a sealed moisture-proof bag, at -18°C/0°F or 5°C/41°F. To accurately establish the exact expiry date, consult the box label.

Shelf Life¹: 6 months at 5°C/41°F (from date of manufacture).

¹ Shelf Life: the maximum storage life for HexPly® prepreg, when stored continuously, in a sealed moisture-proof bag, at -18°C/0°F or 5°C/41°F. To accurately establish the exact expiry date, consult the box label.

Out Life²: 6 weeks at Room Temperature.

² Out Life: the maximum accumulated time allowed at room temperature between removal from the freezer and cure.

Prepreg should be stored as received in a cool dry place or in a refrigerator. After removal from refrigerator storage, prepreg should be allowed to reach room temperature before opening the polyethylene bag, thus preventing condensation. (A full reel in its packing can take up to 48 hours).

Precautions for Use

The usual precautions when handling uncured synthetic resins and fine fibrous materials should be observed, and a Safety Data Sheet is available for this product. The use of clean disposable inert gloves provides protection for the operator and avoids contamination of material and components.

Important

All information is believed to be accurate but is given without acceptance of liability. All users should make their own assessment of the suitability of any product for the purposes required. All sales are made subject to our standard terms of sale which include limitations on liability and other terms

For more informations

Hexcel is a leading worldwide supplier of composite materials to aerospace and industrial markets.

Our comprehensive range includes:

- HexTow® carbon fibers
- HexForce® reinforcements
- HiMax™ multiaxial reinforcements
- HiTape™ advanced reinforcements
- HexPly® prepregs
- HexMC® molding compounds
- HexFlow® RTM resins
- Redux® adhesives
- HexTool® tooling materials
- HexWeb® honeycombs
- Acousti-CAP® sound attenuating honeycomb
- Engineered core
- Engineered products

For US quotes, orders and product information call toll-free 1-800-688-7734. For other worldwide sales office telephone numbers and a full address list, please go to:

<http://www.hexcel.com/Resources/DataSheets/Prepreg>

© 23/02/2021 | Hexcel Corporation - All rights reserved. Hexcel Corporation and its subsidiaries ("Hexcel") believe that the technical data and other information provided herein was materially accurate as of the date this document was issued. Hexcel reserves the right to update, revise or modify such technical data and information at any time. Any performance values provided are considered representative but do not and should not constitute a substitute for your own testing of the suitability of our products for your particular purpose. HEXCEL MAKES NO WARRANTY OR REPRESENTATION, EXPRESS OR IMPLIED, INCLUDING BUT NOT LIMITED TO THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, AND DISCLAIMS ANY LIABILITY ARISING OUT OF OR RELATED TO, THE USE OF OR RELIANCE UPON ANY OF THE TECHNICAL DATA OR INFORMATION CONTAINED IN THIS DOCUMENT.