

EN Product Information

Elan-tech®

AS 46/AW 46 100:80

Cartridges kit ADH 46.46

Slow curing epoxy adhesive. Excellent Peeling resistance

ELANTAS EUROPE Sales offices:

Strada Antolini n°1 loc. Lemignano
43044 Collecchio (PR)
Italy
Tel +39 0521 304777
Fax +39 0521 804410

Grossmannstr. 105
20539 Hamburg
Germany
Tel +49 40 78946 0
Fax +49 40 78946 349

info.elantas.europe@altana.com
www.elantas.com

Structural adhesive	Resin AS 46	Hardener AW 46	Mixing ratio by weight 100:80
Cartridges kit	ADH 46.46		Mixing ratio by volume 100:100

Application: Adhesive for heterogenous materials: wood, composite materials, glass, ceramic and plastics.

Processing: Application by brush, by spatula or with mixing/dispensing devices. Room temperature or hot curing.

Description: Two components epoxy system with excellent Peeling resistance. Slightly thixotropic. Solvent free. The system produces bonding resilient. The system is RoHS compliant (European directive 2002/95/EC) and the new RoHS Directive 2011/65/EU (RoHS 2) entered into force on 21 July 2011 and requires Member States to transpose the provisions into their respective national laws by 2 January 2013.

SYSTEM SPECIFICATIONS

Resin

Viscosity at:	25°C	IO-10-50 (ISO3219)	mPas	38.000	50.000
---------------	------	--------------------	------	--------	--------

Hardener

Viscosity at:	25°C	IO-10-50 (ISO3219)	mPas	14.000	24.000
---------------	------	--------------------	------	--------	--------

TYPICAL SYSTEM CHARACTERISTICS

Processing Data

Colour resin					Milky
Colour hardener					Amber
Mixing ratio by weight		for 100 g resin	g		100:80
Mixing ratio by volume		for 100 ml resin	ml		100:100
Density	25°C Resin	IO-10-51 (ASTM D 1475)	g/ml	1,14	1,18
Density	25°C Hardener	IO-10-51 (ASTM D 1475)	g/ml	0,95	0,99
Pot life	25°C (50mm;200ml)	IO-10-53 (*)	min	40	60
Exothermic peak	25°C (50mm;200ml)	IO-10-53 (*)	°C	105	125
Initial mixture viscosity at:	25°C	IO-10-50 (ISO3219)	mPas	20.000	32.000
Gelation time	25°C (1mm)	IO-10-88 (ASTM D5895-03)	h	5	6
Setting time	25°C 0,1 mm	(*)	h		6 - 8
Suggested curing cycles		(**)			3hrs at 50°C

Cartridges kit ADH 46.46

TYPICAL CURED SYSTEM PROPERTIES

Properties determined on specimens cured: 3hrs at 50°C

			Amber	
Colour			1,10	1,14
Density 25°C		IO-10-54 (ASTM D 792)	g/ml	
Glass transition (Tg)	24h RT	IO-10-69 (ASTM D 3418)	°C	48 54
	16h 40°C		°C	51 57
	3h 50°C		°C	54 60
Shear strength by tension:				
- Aluminium cured 16h 40°C (tested RT)		IO-10-80 (ASTM D 1002)	MPa	20 25
- Inox steel AISI 316 cured 16h 40°C (tested RT)			MPa	21 26
- PVC cured 3h 50°C (tested RT)			MPa	6,5 7,5
- PCcured 3h 50°C (tested RT)			MPa	3,5 4,5
- PMMA cured 3h 50°C (tested RT)			MPa	3,5 4,0
- POM cured 3h 50°C (tested RT)			MPa	2,5 3,0
- Inox steel AISI 316 cured 24h 20°C (tested RT)			MPa	15 28
- Inox steel AISI 316 cured 7 days 20°C (tested RT)			MPa	21 26
- Inox steel AISI 316 cured 16h 40°C tested at RT after 96 h (salt spray)			MPa	23,5 28,5
Flexural strength		IO-10-66 (ASTM D 790)	MN/m ²	56 64
Maximum strain		IO-10-66 (ASTM D 790)	%	4,5 6,5
Strain at break		IO-10-66 (ASTM D 790)	%	>15
Flexural elastic modulus		IO-10-66 (ASTM D 790)	MN/m ²	1.600 2.000
Tensile strength		IO-10-63 (ASTM D 638)	MN/m ²	36 44
Elongation at break		IO-10-63 (ASTM D 638)	%	4 6
Peeling strength:				
- Aluminium cured 3h 50°C (tested RT)		ASTM D 1876	N/cm	48 58

IO-00-00 = ELANTAS Europe's test method. The corresponding international method is indicated whenever possible.

nd = not determined na = not applicable RT = TA = laboratory room temperature (23±2°C)

Conversion units: 1 mPas = 1 cPs 1MN/m² = 10 kg/cm² = 1 MPa

(*) for larger quantities pot life is shorter and exothermic peak increases

(**) the brackets mean optionality

(***) The maximum operating temperature is given on the basis of laboratory information available being it function of the curing conditions used and of the type of coupled materials. For further possible information see post-curing paragraph.

Cartridges kit ADH 46.46

- Instructions:** Prepare the surfaces to be bonded by removing moisture, dust, dirt and loose parts. For metals is normally enough a mechanical abrasion or sand blasting followed by degreasing with acetone. When gluing composite parts it is not required any specific surface treating other cleaning with acetone. In case of plastic substrate it is important to check its solvent resistance before cleaning. Generally is suggested a light sanding followed by cleaning with alcohol. Plasma or corona treatment will improve adhesion and consequently bonding strength: it's recommended in case of specific needs. Add the appropriate amount of hardener into the resin and mix carefully using a slow speed stirrer or by hand with a spatula. Apply the adhesive in a homogeneous thickness maintaining a uniform contact pressure on the joint. Before setting , the adhesive is moisture and carbon dioxide: once applied cover the joined parts as soon as possible or, better, hot cure if possible. Further general information are available in the brochure "Elan-tech Adhesive & Sealants".
- Curing/Post-curing:** Post curing is always advisable for RT curing systems in order to stabilize the component and to reach the best properties. It is necessary when the component works at a high temperature.
- Storage:** Epoxy resins and their hardeners can be stored for two years in the original sealed containers stored in a cool, dry place. The hardeners are moisture sensitive therefore it is good practice to close the container immediately after each use.
- Handling precautions:** Refer to the safety data sheet and comply with regulations relating to industrial health and waste disposal.

emission date: February 2016
revision n° 00

The information given in this publication is based on the present state of our technical knowledge but buyers and users should make their own assessments of our products under their own application conditions.