

EN

Preliminary Technical Data Sheet

Elan-tech®**EC 157.1 BIO/W 152 LR**

100:30

2K Unfilled epoxy system

ELANTAS Europe Sales offices:

Collecchio (PR) 43044 - Italy
Strada Antolini n° 1 loc. Lemignano
Tel +39 0521 304777 Fax +39 0521 804410

Hamburg 20539 - Germany
Großmannstrasse. 105
Tel +49 40 78946 0 Fax +49 40 78946 349

info.elantas.europe@altana.com
www.elantas.com/europe



Product description

- 2K unfilled epoxy system
- Bio-based part resin
- Very low viscosity
- Low reactivity hardener
- Good fibers wettability
- High modulus
- Thermally resistant up to 70°C

Areas of application

High performance composite parts. Available for large and medium thickness structure, such as sailing boats, shipyard structures, sport equipments and devices.

Processing methods

Vacuum infusion of glass, aramid or carbon fiber fabrics & multiaxials. Suitable for application with natural fibers (flax). Room temperature curing. Post curing needed to achieve the proper thermal resistance.

Curing/Post-curing

Post-curing is always advisable for Room Temperature curing system in order to stabilize the component and/or to reach the best properties. It is necessary when the component works at high temperature. Recommended post curing rump-up: 10°C/hour. Cool it down slowly. The rate of heating and the indicated post-curing time are referred to laboratory specimen size. Users should evaluate the best conditions of curing or post-curing depending on the component size and shape. For big size components it is advisable to decrease the thermal gradient and increase the post-curing time.

Storage and stability

Unfilled epoxy resin and its amine based hardener can be stored for one year in the original sealed containers in a cool, dry place. The hardener is moisture sensitive therefore it is good practice to close the container immediately after each use.

Handling precautions

Refer to the safety data sheet and comply with regulations relating to industrial health and waste disposal.

Typical product properties

EC 157.1 BIO

| Properties | Conditions | Test Method | Value | M/U |
|------------|------------|------------------------|-------------|-------|
| Colour | | -- | Amber | |
| Viscosity | 25 °C | IO-10-50 (ISO 3219) | 600 ÷ 900 | mPa·s |
| Density | 25 °C | IO-10-51 (ASTM D 1475) | 1,13 ÷ 1,17 | g/ml |

W 152 LR

| Properties | Conditions | Test Method | Value | M/U |
|------------|------------|------------------------|-------------|-------|
| Colour | | -- | Pale yellow | |
| Viscosity | 25 °C | IO-10-50 (ISO 3219) | 20 ÷ 40 | mPa·s |
| Density | 25 °C | IO-10-51 (ASTM D 1475) | 0,93 ÷ 0,97 | g/ml |

Typical system properties

| Properties | Conditions | Test Method | Value | M/U |
|---------------------------|------------------------|---------------------------|-----------|-------|
| Mix Ratio by weight | | -- | 100 : 30 | g |
| Mix Ratio by volume | | -- | 100 : 37 | ml |
| Initial mixture viscosity | 25 °C | IO-10-50 (ISO 3219) | 350 ÷ 550 | mPa·s |
| Exothermic peak | 25 °C - 50 mm - 200 ml | IO-10-53 (*) | 135 ÷ 145 | °C |
| Pot life | 25 °C - 50 mm - 200 ml | IO-10-53 (*) | 145 ÷ 215 | min |
| Gel time | 25 °C - 1 mm | IO-10-88 (ASTM D 5895-03) | 15 ÷ 17 | hrs |

Typical cured system properties

| Properties | Conditions | Test Method | Value | M/U |
|------------------------|----------------------|------------------------|----------------------|------------|
| Specimens curing cycle | | -- | 24 h RT + 15 h 60 °C | |
| Density (solid) | 25 °C | IO-10-54 (ASTM D 792) | 1,08 ÷ 1,12 | g/ml |
| Hardness | 25 °C | IO-10-58 (ASTM D 2240) | 81 ÷ 85 | Shore D/15 |
| Glass Transition (Tg) | 7 days RT | IO-10-69 (ASTM D 3418) | 55 ÷ 60 | °C |
| | 24 h RT + 15 h 60 °C | | 73 ÷ 78 | °C |
| | 24 h RT + 15 h 50 °C | | 67 ÷ 73 | °C |
| Maximum Tg | 24 h RT + 15 h 60 °C | IO-10-69 (ASTM D 3418) | 73 ÷ 78 | °C |

Typical mechanical properties in cured condition

| Properties | Conditions | Test Method | Value | M/U |
|--------------------------|------------|-----------------------|----------------------|-------------------|
| Specimens curing cycle | | -- | 24 h RT + 15 h 60 °C | |
| Flexural strength | 25 °C | IO-10-66 (ASTM D 790) | 90 ÷ 110 | MN/m ² |
| Strain at maximum stress | 25 °C | IO-10-66 (ASTM D 790) | 4,0 ÷ 6,0 | % |
| Strain at break | 25 °C | IO-10-66 (ASTM D 790) | 8 ÷ 12 | % |
| Flexural elastic modulus | 25 °C | IO-10-66 (ASTM D 790) | 2600 ÷ 3200 | MN/m ² |
| Tensile strength | 25 °C | IO-10-63 (ASTM D 638) | 70 ÷ 80 | MN/m ² |
| Nominal strain at break | 25 °C | IO-10-63 (ASTM D 638) | 5,0 ÷ 8,0 | % |
| Compressive strength | 25 °C | IO-10-72 (ASTM D 695) | 65 ÷ 80 | MN/m ² |

IO-00-00 = Elantas Europe internal test method. The correspondent international method is indicated whenever possible; nd = not determined; na = not applicable; RT = TA = laboratory room temperature (23±2°C); conversion units: 1 mPas = 1 cPs 1MN/m² = 10 kg/cm² = 1 MPa

(*) for larger quantities pot life is shorter and exothermic peak increases; (**) the brackets mean optionality; (***) the maximum operating temperature is given on the basis of laboratory information available being it function of the curing conditions used and of the type of coupled materials. For further possible information see post-curing paragraph.

Product of ELANTAS Europe. Our advice given verbally or in writing is based on the present state of our technical knowledge, but is intended as information given without obligation, also with respect to any protective rights held by third parties. It does not relieve your own responsibility to check the products for their suitability to the purposes and processes intended and in accordance with the technical sheets of the products. The application usage and processing of the product are beyond our control and will completely fall into the scope of responsibility of buyers and users. Should there nevertheless be a case of liability from our side, this will be limited to any damage equivalent to the value of the merchandise delivered by us. Naturally, we assume responsibility for the unobjectionable quality of our products, as defined in our general terms and condition. Product conformity is guaranteed by properties defined in sales specification. Typical properties do not constitute part of the agreed product property or sales specification. Deviation from typical properties does not constitute non-conformity of the product. Typical properties are provided for general information purpose and as a guideline for the choice of the product; they are subject to variation related to i.e. curing cycles, specimen preparation, batch to batch variability, etc. unless specifically agreed with customers.