

Technical Datasheet

Ashland Performance Materials

MAXGUARD[®]
PREMIUM GELCOATS

MAXGUARD[®] GN // H/S Premium Iso/NPG Gelcoat

MAXGUARD GN // H/S are premium gelcoats based on a special isophthalic/NPG resin. The base resin and the gelcoat formula are optimized to give final products excellent mechanical and weathering properties. MAXGUARD GN // H/S premium gelcoat surfaces are hard, glossy and tough and they are highly resistant to UV-radiation, gloss deterioration and hydrolysis.

Typical liquid gelcoat properties

Properties at 23 °C	H (Brush)		S (Spray)	
	Value	Value	Unit	Method
Viscosity, Brookfield RV5, 10 rpm	13000	7000	mPas	ISO 2555
Viscosity, cone&plate	900	250	mPas	ISO 2884
Geltime, 2% MEKP-50	13	7	min	ASTM D2471

Typical gelcoat base resin properties

Properties (postcure 24h at 50 °C)	Value	Unit	Method
Tensile strength	70	MPa	ISO 527
Tensile modulus	3600	MPa	ISO 527
Elongation at break	3,5	%	ISO 527
Flexural strength	125	MPa	ISO 178
Flexural modulus	3600	MPa	ISO 178
Heat deflection temperature (1,81 MPa) *)	90	°C	ISO 75 (A)
Hardness	41	Barcol	ASTM D2583
Water absorption , 28 days / 7days/ 24 hours	75 / 42 / 11	mg/sample	ISO 62

*) post cured 24h at 50 °C + 3h at 80°C

Application and use

MAXGUARD GN // H/S premium gelcoats are recommended for use in the sanitary, marine or similar industries with high demand of surface properties of composite products.

Certificates and approvals

MAXGUARD GN // H/S are approved by classification societies like Det Norske Veritas, Lloyd's Register and Germanischer Lloyd's for construction of small crafts.

Wash basins with Maxguard GN // H/S gelcoat surfaces complies with the American Thermal Shock test ANSI Z124.3-86 for sanitary applications.

The manufacturing, quality control and distribution of products, by Ashland Performance Materials, are complying with one or more of the following programs or standards: Responsible Care, ISO 9001, ISO 14001 and OHSAS 18001.



Responsible Care*

Ashland is committed to the continuous evolution of technology and service solutions that promote health, safety and environmental protection around the world.

* Registered service mark of the American Chemistry Council. © Registered trademark and [™] trademark of Ashland Inc.

ASHLAND[®]
With good chemistry great things happen.™

Technical Datasheet

Ashland Performance Materials

MAXGUARD[®]
PREMIUM GELCOATS

MAXGUARD[®] GN // H/S Premium Iso/NPG Gelcoat

Handling and storage For good handling and working practices, see Ashland "Gelcoat Handling Guide". It is highly recommended that all materials are stored at stable temperature under 25 °C preferably indoors, and away from direct sunlight. A high quality methyl ethyl ketone peroxide (MEKP) catalyst should be used between 1.5 - 2.5%. The gelcoat with the catalyst must be gently stirred before taken in use.

Shelf life of MAXGUARD GN // H or MAXGUARD GN // S is 5 months.

Prolonged storage or storage outside of recommended conditions can influence gelcoat liquid properties like viscosity and gel time and it is recommended to test these properties before starting application

Notice

All information presented herein is believed to be accurate and reliable, and is solely for the user's consideration, investigation and verification. The information is not to be taken as an express or implied representation or warranty for which Ashland assumes legal responsibility. Any warranties, including warranties of merchantability or non-infringement of intellectual property rights of third parties, are herewith expressly excluded.

Since the user's product formulations, specific use applications and conditions of use are beyond the control of Ashland, Ashland makes no warranty or representation regarding the results which may be obtained by the user. It shall be the responsibility of the user to determine the suitability of any of the products mentioned for the user's specific application.

Ashland requests that the user reads, understands and complies with the information contained herein and the current Material Safety Data Sheet.



Responsible Care*

Ashland is committed to the continuous evolution of technology and service solutions that promote health, safety and environmental protection around the world.
* Registered service mark of the American Chemistry Council. © Registered trademark and [™] trademark of Ashland Inc.

ASHLAND[®]
With good chemistry great things happen.[™]