

Armacell GmbH

Robert Bosch Str. 10 D-48153 Münster Telefon (0251) 7603-0 Telefax (0251) 7631-491 testing.muenster@armacell.com

Product Testing Department

1 of 1

TESTREPORT

Determination of burning behaviour according to: ISO 9772.3 / UL94

PRODUCT IDE	NTIFICATION	TEST PROCEDURE			
product name	PET AC-100	who sampled	production staff		
nominal dimension	25-099	where	production line		
nominal thickness [mm]	25	conditioning	24h at room temperature		
factory	Armacell Thimister	number of test specimens	5		
manufacturer or supplier	Armacell	length of test specimens	150 mm		
production code number	334280	width of test specimens	50 mm		
type of product	sheet	Wall Thickness	25 mm		
packaging	carton	test date	21.04.2010		
form, in which the product arrived at the laboratory	1 m²	chosen apparatus	UL94 chamber		
presence of surface skin	smooth				
facing	no facing				
remarks	test number PBTT – 2 - 2010				

RESULTS

sample	wall thickness	burning time	burning distance	burnt length	UL-94
	[mm]	[sec]	[mm]	[mm]	CLASS
PET AC-100	25	46	11,4	36	HBF

The material fulfils the requirements regarding UL-94 Class HBF

mace,

lesting |

prepared:

R.Eckert

approved:

M.Klein

21.04.2010