



P.O. Box 588, Orpington, Kent BR6 7XU, UK
Tel: +44 (0) 1959 573778
Fax: +44 (0) 1959 570939
Email: dosunedosune@aol.com
www.flexokore.co.uk
VAT. No. 826947683

MECHANICAL PROPERTY TABLE

FLEXOKORE®

Typical properties for FLEXOKORE® end grain balsa

Nominal Density	Lb/ft ³ Kg/m ³	9.3 150
Compressive Strength ASTM C365	Psi MPa	1,850 12.80
Compressive Modulus ASTM C365	Psi Mpa	590,000 4,070
Shear Strength ASTM C273	Psi MPa	432 2.98
Shear Modulus ASTM C273	Psi Mpa	23,100 159
Tensile Strength ASTM C297	Psi Mpa	1,900 13.10
Thermal Conductivity ASTM C177 @ 75°F	BTU inch/hr/ft ² /°F W/m °K	0.450 0.0649

The above table gives average values. Balsa is a natural product and balsa densities vary. For sandwich panel design minimum values should be used.

This information is believed to be correct but no warranty is made, either expressed or implied, regarding its accuracy or results obtained from the use of such information. Also that any such use will not infringe any patent is made.

